

DERWENT CHEMICAL PATENTS INDEX

L34 ANSWER 1 OF 10 WPIDS COPYRIGHT 1997 DERWENT INFORMATION LTD

AN 97-358584 [33] WPIDS

DNN N97-297798 DNC C97-115359

TI Heat sensitive recording medium useful for uniform image formation - comprises substrate with heat sensitive recording layer containing a leuco dye and developer, useful especially for high quality images.

DC A25 A89 E17 E23 G05 P75 T04

PA (OJIP) OJI PAPER CO

CYC 1

THIS CITATION WAS RETRIEVED IN BOTH MARPAT AND MARKUSH/DARC

PI JP 09150577 A 970610 (9733)* 6 pp B41M005-26 <--

ADT JP 09150577 A JP 95-311042 951129

PRAI JP 95-311042 951129

IC ICM B41M005-26

AB JP09150577 A UPAB: 970813

A medium comprises a substrate provided with a heat sensitive recording layer containing a leuco dye and a developer as the main component.

The heat sensitive recording layer contains, further, 0.1-1.0 wt. % of acetylene glycol compound of formula (I) based on the total solid matter of the layer.

$$R_1-C(CH_3)(R_2)-C \text{ triple bond } C-C(CH_3)(R_2)-R_1 \quad (I)$$

R₁ = methyl, ethyl, propyl or butyl;

R₂ = -(OC₂H₄)NOH or -(OC₃H₆)NOH; and

n = 1-10.

USE - Used as a heat sensitive recording medium having high quality of formed images.

ADVANTAGE - The heat sensitive recording medium uses synthetic paper as the substrate and the heat sensitive recording layer is free from unevenness in coating. Formed images have no unevennesses.

Dwg. 0/0

FS CPI EPI GMPI

FA AB; DCN

MC CPI: A10-E08A; A12-L05A; E10-E04J; G06-F08; G06-F08A

EPI: T04-G03A1

L34 ANSWER 2 OF 10 WPIDS COPYRIGHT 1997 DERWENT INFORMATION LTD

AN 94-354468 [44] WPIDS

CR 84-222640 [36]

DNC C94-161487

TI Mfr. of cement mortar-concrete hardening material - by kneading raw material with water-soluble acetylene alcohol.

DC A93 E19 L02

PA (NICE) NIPPON CEMENT KK

CYC 1


PI JP 06279081 A 941004 (9444)* 9 pp C04B024-02 <--

ADT JP 06279081 A JP 91-39336 910208

PRAI JP 91-39336 910208

IC ICM C04B024-02

ICS C04B024-32; C04B024-42; C04B028-02



AB JP06279081 A UPAB: 950705

A manufacturing process for cement mortar-concrete hardening material in which the raw material is kneaded by adding 0.5-10 wt. %